

Outside Diameter		Wall Thickness		Material Grade	Weight Threaded & Coupled			Test Pressure psi J55 & K55	Thread Type	
Inch	Metric	in	mm	Seamless/ERW	lb/ft	kg/ft	kg/m	PSI	Coupled	Flush
4 1/2"	114.3	0.224	5.69	API 5CT J55	10.5	4.67	15.63	3000	BTC	SFJ
5 1/2"	139.7	0.275	6.99	API 5CT J55	15.5	7.03	23.07	3000	BTC	SFJ
6 5/8"	168.3	0.288	7.32	API 5CT J55	20	9.07	29.76	3000	BTC	SFJ
7"	177.8	0.317	8.05	API 5CT J55	23	10.43	34.23	3000	BTC	SFJ
8 5/8"	219.08	0.352	8.94	API 5CT J55	32	14.51	47.62	3000	BTC	SFJ
9 5/8"	244.48	0.352	8.94	API 5CT J55	36	16.33	53.57	3000	BTC	SFJ
10 3/4"	273.05	0.400	10.16	API 5CT J55	45.5	20.64	67.71	2500	BTC	SFJ
13 3/8"	339.73	0.380	9.65	API 5CT J55	54.5	24.72	81.1	1900	BTC	SFJ